



TESTING TECHNOLOGY FOR SPORT

LABORATORY ANALYSIS REPORT

Sample Reference **GommaAmica® Powerfill EPDM**

Report Number 10061/6461

Report Status Final

Issue Date 16/01/2020

Client ELASTRADE S.R.L.
Via Matteotti, 45/1
64028 Silvi (Te)
Italia

FOREWORD

1. This report has been prepared by Sports Labs limited with all reasonable skill, care and diligence within the terms of the contract with the Client and within the limitations of the resources devoted to it.
2. This report is confidential to the Client and Sports Labs Limited accepts no responsibility whatsoever to third parties to whom this report, or any part thereof, is made known. Any such party relies upon the report at their own risk.
3. This report shall not be used for engineering or contractual purposes unless signed by the Author and the Checker and unless the report status is "Final".
4. *Not all tests carried out are within our scope of ISO 17025 Accreditation.
5. Comments and opinions are out with the scope of our ISO 17025 accreditation



HEADQUARTERS

Sports Labs Ltd
1 Adam Square,
Brucefield Industry Park
Livingston EH54 9DE
Scotland, United Kingdom

Tel: +44 (0) 1506 444 755
Email: info@sportslabs.co.uk
Web: www.sportslabs.co.uk

REGIONAL LOCATIONS

- USA
- Morocco
- Turkey
- South Africa
- Netherlands
- Belgium
- Norway
- Israel



1.0 INTRODUCTION

This report details the test results from the sample of GommaAmica® Powerfill EPDM submitted to our Laboratory for analysis according to the following methods:

REQUESTED TEST METHODS

- * DIN 18035-7:2014 Chemical Analysis

*Not all tests carried out are within our scope of ISO 17025 Accreditation.

⁽¹⁾ This testing was carried out by sub-contracted specialist laboratories under their report number L038/0120-1.

2.0 SAMPLE REFERENCE

Test Components

Component No.	Description
1	GommaAmica® Powerfill EPDM

Prepared By Craig Melrose
Laboratory Manager
16/01/2020


.....

Checked By Sean Ramsay
Associate Director
16/01/2020


.....

3.0 TEST RESULTS

DIN 18035-7:2014 HEAVY METAL ANALYSIS *

Test Parameter	Test Method	DIN18035-7 Specification Requirement	Result	Pass/Fail
Dry Matter	DIN ISO 11465*	-	99.8	-
EOX	DIN 38414-S17*	≤ 100 mg/kg	2.94	Pass
Ph-Wert	DIN EN ISO 10523-C5	≤100 mg/kg	8.59	Pass
DOC (24hr)	BS EN 1484*	≤ 50 mg/l	37.8	Pass
Lead	BS EN ISO 11885*	≤ 0.025 mg/l	< QL	Pass
Cadmium	BS EN ISO 11885*	≤ 0.005 mg/l	< QL	Pass
Chromium	BS EN ISO 11885*	≤ 0.05 mg/l	< QL	Pass
Chromium VI	DIN 38405-D24*	≤ 0.008 mg/l	< QL	Pass
Mercury	ICP-OES*	≤ 0.001 mg/l	0.0001	Pass
Tin	BS EN ISO 11885*	≤ 0.04 mg/l	< QL	Pass
Zinc (24hr)	BS EN ISO 11885*	≤ 0.5 mg/l	0.0245	Pass

< QL Result below quantification limit (ie. below measuring capabilities of test apparatus)

End of Report

*Not all tests carried out are within our scope of ISO 17025 Accreditation.